



**West Yorkshire
Materials Testing
Service**

PO Box 5, Morley, LS27 0QP Page 1 of 1
Nepshaw Lane South, Morley, Leeds
Tel 0113 253 0241 Fax 0113 252 7029
Head of Laboratory G. Briggs C. Text ATI

Client: Winter Creation AG
Alliothstrasse 60
Postfach 948
4142 Munchenstein 1
Switzerland

Entry No: 47698 (Amended)

Date received: 29/07/2011

Client's Description: Sample of fabric: Micropore®

TEST REPORT

Test Required: Flammability

Pre-treatment: None

Conditioning: A minimum of 24 hours at 50 +/- 5% Relative Humidity, 23 +/- 2°C

Method of Test: BS EN 1021-1:2006 – smouldering cigarette
BS EN 1021-2:2006 – match flame equivalent

Date of Test: 04/08/2011

Ignition Source	Observations	Result
Smouldering cigarette	No flaming or progressive smouldering was observed within one hour of placement of the cigarettes.	PASS
Match flame equivalent	No flaming or progressive smouldering was observed after removal of the butane flame.	PASS

Note: A 35 kg/m³ CMHR Foam (Carpenters RX36-125) was used as the filling

The above tests relate only to the ignitability of the combination of materials under the particular conditions of test; they are not intended as a means of assessing the full potential fire hazard of the materials in use.

-----End of Document-----

This is hereby certified to be a correct return of the tests made of the items referred to herein.



1104

G Briggs, Head of Laboratory
Date of original 5th August 2011
Date of amendment 17th February 2012

- ◆ Unless instructed otherwise by the client sample remnants will be disposed of after 28 days
- ◆ Test marked (*) in this certificate are not included in the UKAS Accreditation Schedule for this Laboratory
- ◆ Opinions and interpretations expressed herein are outside the scope of UKAS accreditation.
- ◆ This Certificate relates only to the sample received and, unless that sample has been drawn by the staff of this laboratory, or its agent, and endorsed accordingly, any application of the result to a bulk quantity or other material is entirely the responsibility of the client.

